

Produktdatenblatt

Langenthaler Str. 4
69434 Hirschhorn/Neckar
Germany
phone 00-49-6272-689-0
fax 00-49-6272-689-30

Version: 10ZT09E

dekofilm

Available are 4 impregnating machines with working widths of 150 – 260 cm.

Overlay -, Barrier- and Decorative Papers

of 60 – 260 cm width are impregnated on those machines with melamine -, melamine urea – and urea resins. These papers are destined for the production of high pressure laminates (also postforming), laminated particleboards, form-pressed particleboards (according to the *Werzalit* process), form-pressed laminates (tray) as well as surface-protected veneer sheets. The weight per unit area of the raw papers is, depending on the use, between 25 and 220 g, the resin contents lie between 80 and 300%.

Phenol - impregnated Kraft Papers

are produced up to a width of 174 cm and paper weights of 80 – 220 g, with resin contents of 45 – 100%.

The reactivation of the impregnated papers which is necessary for the pressing procedure will be employed individually according to each requirement of the processing plant.

Form of Delivery

Size in all widths between 60 and 260 cm, up to 100 cm length on one-way pallets or pallets for multiple use. Material on rolls up to 220 cm width, on cores with an inside diameter of 150 mm possible.

Storage

Dekofilm should be stored in a closed room with a temperature of 18-25°C and 50-60% relative humidity. Furthermore, they have to be stored full-laminar and horizontally with a distance of 200 mm to the ground.

Dekofilm – papers

- are to be protected from moisture
- should not be exposed to direct sunlight
- should not be stored in a warm-air-stream

If removing only parts of the papers from the packaging, the covering-foil should be re-sealed.

Packaging

Europe: PE

Overseas: Alu and PE